

Product Data Sheet



Panache
PAINT

Panache Bonding Liquid

No	JP13
Date	07/21

Panache products are manufactured to the highest quality and performance standards to ensure complete customer satisfaction.

DESCRIPTION

Panache Supreme Bonding Liquid is a solvent-based sealer and binder for bonding chalky surfaces. It can be applied to interior and exterior non-alkaline friable surfaces such as gypsum plaster. May be used over old or aged cement plaster. Increases substrate strength for optimum durability of all finishing coats.

PRODUCT USES

- Suitable for sealing very porous surfaces such as Asbestos/Fibre Cement and Gypsum Plaster.
- Binding Powdery/Chalked PVA or Lime Washed surfaces
- Suitable for alkaline surfaces such as fresh cement plaster.
- Ideal for Interior & Exterior Walls.

PRODUCT BENEFITS

- Alkali resistant
- Excellent penetrating and bonding sealer
- Increase strength for durability
- Quality Guaranteed

SURFACE PREPARATION

New Surfaces: Surface/s must be thoroughly clean, dry and in sound condition before painting.

Concrete/Cement Plaster: Apply one coat of Panache Bonding Liquid and wait 16 - 18 hours, then apply two coats of your desired Panache topcoat with correct drying time between coats.

Asbestos/Fibre Cement: Apply one coat of Panache Bonding Liquid and wait 16 - 18 hours, then apply two coats of your desired Panache topcoat with correct drying time between coats.

Gypsum Plaster (Rhinolite/Rhinoglide): Apply one coat of Panache Bonding Liquid and wait 16 - 18 hours, followed by two coats of your desired Panache topcoat with correct drying time between coats.

PREVIOUSLY PAINTED SURFACES

Thoroughly clean and prepare surface by removing all dirt, grease, grime and flaking paint before painting. Powdery surfaces must be treated with one coat of Panache Bonding Liquid and wait 16 - 18 hours, prior to applying two coats of your desired Panache Topcoat with correct drying time between coats. Enamel based surfaces must be cleaned and prepared correctly. Sand lightly and apply one coat of Panache Universal Undercoat and wait 16 - 18 hours, followed by two coats of Panache Gloss Enamel with correct drying time between coats.

APPLICATION

Stir the contents thoroughly before use. This product should be applied without thinning. For colour consistency, ensure that batch numbers are the same on all cans. Apply this product with a paintbrush or (mohair) paint roller and allow 16-18 hours drying time between coats. Allow paint to cure (hard dry) for 7 days before attempting to clean the surface. Do not apply when rain is imminent. Clean tools (brushes & rollers) with Mineral Turpentine immediately after use.

COLOUR RANGE

Available in Clear

PACKAGING:

Packaging: 1L, 5L, 20L

SPREADING RATE

This product will cover approximately 10-12m² /litre, depending on surface porosity.

TECHNICAL DATA

Type	Alkyd
Finish	Smooth Haze
Drying Time @ 25°C	Touch Dry: 4 - 6 Hours Hard Dry: 16 - 18 Hours
Re-coating Time	16 - 18 Hours
Viscosity	10-15 seconds
Specific Gravity	-/+ 0.83kg / Litre
Storage	Dry and Cool area

PRECAUTIONS

Do not apply if rain is imminent.

Apply at an ambient temperature of 5 to 35°C.

Keep out of reach of children.

Wash hands with Mineral Turpentine immediately after use.

Skin or Eye contact: clean with fresh water and consult a physician if necessary.

Do not paint before 9:00 and after 15:30.

TOOL CHECKLIST

Paintbrush & Paint Roller Tray Set; Plastic Drop Sheet; Mutton Cloth; Sandpaper; Masking Tape; Crack Filler; Paint Scraper; Stepladder and Mineral Turpentine.

QUALITY GUARANTEE

This product is quality controlled and packed to the highest standard.

Medal and Jack's Paint accepts no responsibility, nor accountability for either workmanship in surface preparation or the application of our products.

The information given in this Product Data Sheet is based on controlled laboratory tests and many years of experience. It is given in good faith, but no guarantee of any performance characteristic is given or implied. Jacks Paint cannot be held liable for consequential damage of whatsoever nature that may arise from the use of Panache products. Paint technology is continuously being developed and Jacks Paint reserves the right to update product specifications without prior notice. Contact Jacks Paint for further details on 0860 522 577.

